

# **Technical Data Sheet**

## GFS-4

#### **General Description**

- Daylight and ultra-violet responsive fluorescent soluble toner for solvent based formulations.
- A dyed/pigmented thermoplastic glycol-urilsulphonamide- paraformaldehyde resin.

#### Applications

- Solvent based inks for gravure, flexo and inkjet.
- Solvent based paints and powder coatings.

#### **Product Features**

- GFS-4 soluble toners are transparent and should be printed on white background or over a white ink to achieve the maximum fluorescent brightness.
- GFS-40 & GFS-48 can be blended to achieve intermediate fluorescent colors.

#### Standard Color

| Product Name | Description |
|--------------|-------------|
| GFS-40       | Yellow      |
| GFS-47       | Pink        |
| GFS-48       | Magenta     |

### Packaging:

1 box = 20 kgMOQ = 20 kg

#### Storage & shelf life:

120 months when kept in closed original packaging in a dry place at ambient temperature.

Safety & regulatory: Safety Data Sheet available on request.

- Compatible with most resins used in solvent based flexo and gravure ink formulations, like nitrocellulose(esters), acrylics and polyamides.
- No particles in finished ink due to completely solubility.

| Physical properties               |                 |
|-----------------------------------|-----------------|
| Delivery form                     | Granular powder |
| Particle size (Laser diffraction) | <150.0 µm       |
| Melting point                     | 80 – 115 °C     |
| Specific gravity                  | 1.38 g/ml       |
| Bulking value                     | 0.40 g/ml       |

(1)Test methods and Certificate of Analysis (COA) available on request.

| Processing         |  |  |
|--------------------|--|--|
| Solvent resistance | Completely soluble in a combination of strong polar solvents |  |
|                    | such as alcohols and esters.                                 |  |

Disclaimer: Our technical advice, information, statements, whether given verbally, in writing, or in the form of test results, is offered for your guidance without warranty. No warranty for fitness for a particular purpose is made. This also applies where protective rights of third parties are involved. It does not release the user from obligation to test the suitability of the products and formulas for the intended process and applications. Our guarantee is limited to the consistent quality of our product. Rev:1.1