

Technical Data Sheet

GloPrill® Hyperdispersed Colorants

General Description

GloPrill® is a high-performance fluorescent colorant developed especially for use in polyolefins. Designed with the plastics concentrate/masterbatch producer in mind, these supercharged colorants develop brilliant, clean fluorescent colors and offer superior processing properties. GloPrill® virtually eliminates the problem of plate-out at the blowpin and in the mold cavity. Continuous high-speed production is now possible with minimum downtime. Concentrate and masterbatch formulations can be simplified with the elimination of expensive or hard to handle additives for controlling plate-out and dispersion. The expanded color line includes high-strength GPX products and single-strength GPL colors to simplify formulations.

Available Colors	
Product Code	Color
GPL-11	Aurora Pink
GPL-13	Rocket Red
GPX-14	Fire Orange
GPL-15	Blaze Orange
GPX-17	Saturn Yellow
GPL-19	Horizon Blue
GPL-21	Corona Magenta
GPL-00	Clear

Advantages

- Dust free performance from a super high strength prill
- Cleanest, brightest fluorescent products offered for blow molding and injection molding
- Use at full strength for lowest cost in use or as a replacement for melt-in colorants for custom color matches
- Unsurpassed plate-out performance. At normal molding temperatures, reduces blowpin plate-out or in-mold residue to practically zero.
- Simplify your formulations. Eliminate expensive or hard to handle plate-out packages
- Completely formaldehyde-free
- Faster processing and clean-up

Typical Physical Properties	
Physical Form	Free Flowing Prill
Minimum Processing Temperature	300°F
Heat Stability	550°F
Melt Index per ASTM D1238	10–27g/10 min
Bulk Density	41.8 lbs/ft ³ (0.67g/cm ³)

Disclaimer: Our technical advice, information, statements, whether given verbally, in writing, or in the form of test results, is offered for your guidance without warranty. No warranty for fitness for a particular purpose is made. This also applies where protective rights of third parties are involved. It does not release the user from obligation to test the suitability of the products and formulas for the intended process and applications. Our guarantee is limited to the consistent quality of our product.